



Talc Free Eyeshadow with HSE Green Tea Pigments (French Blue)

Herbal Skin Enhancer (HSE) treated Sericite creates a moist, lubricious skin feel.

Ingredient	INCI Name	Supplier	%
Phase 1			
D-9061/I Hydrophobic Matte Sericite	Mica, Methicone	Color Techniques	23.95
Zinc Stearate 921-G	Zinc Stearate	Brenntag	3.00
HSE GT-0061 Matte Sericite	Mica, Simmondsia Chinensis (Jojoba) Seed Oil, Camellia Sinensis (Green Tea) Leaf Extract, Cetyl Phosphate, Ascorbyl Palmitate	Color Techniques	15.00
E-5100 Ultramarine Blue	Ultramarines	Color Techniques	2.00
A-1403 Black Iron Oxide	Iron Oxides	Color Techniques	2.00
Ascorbyl Palmitate	Ascorbyl Palmitate	DSM	.05
Biron® LF-2000	Bismuth Oxychloride	EMD Performance Materials	5.00
Orgasol® 2002D Nat Cos	Nylon-12	Vantage	5.00
Kaolin 2457	Kaolin	Brenntag	5.00
Phase 2			
Cloisonne® Blue	Mica, Titanium Dioxide, Ferric Ferrocyanide	BASF	30.00
Phase 3			
Wickenol® 131	Isopropyl Isostearate	Alzo	2.95
Mixed Tocopherols	Tocopherol		.05
Xiameter® PMX-200 Silicone Fluid/100 cs	Dimethicone	Dow Chemical	5.00
Optiphen®	Phenoxyethanol, Caprylyl Glycol	Ashland	1.00
			100.00

Continued

Talc Free Eyeshadow With HSE Green Tea Pigments (French Blue)

Manufacturing Procedure:

- 1- Combine Phase 1 with thorough mixing. Mill once.
- 2- Add Phase 2 with thorough mixing.
- 3- Combine Phase 3 with stirring. Spray onto combined Phases 1 and 2 while agitating. Mill with low intensity.